

# PATENT SPECIFICATION

(11) 1 228 592

NO DRAWINGS

- (21) Application No. 14624/68 (22) Filed 27 March 1968  
 (23) Complete Specification filed 3 Feb. 1969  
 (45) Complete Specification published 15 April 1971  
 (51) International Classification B 32 b 5/16, 11/06, 27/10, 5/26, 17/02, 29/06, 11/02, 19/08  
 (52) Index at acceptance  
     B5N 177 179 17X 17Y 20X 20Y 227 228 22Y 239 250  
         252X 252Y 254X 254Y 255X 255Y 280X 280Y  
         282X 282Y 344 345 346 353 37X 402 540  
         542 54X 554 55Y 570 574 577 627 630 635 63X  
         641 654 656 682 690 691 69Y 715 71X 765 769  
         774 791  
     B2E 189 18Y 190 204 209 20Y 211 21Y 23Y 248 24Y  
         287 28Y 305 307 31Y 339 349 361 398 421 461  
         508 53Y 579 622 62Y 65Y 707 708 70Y 725 727  
         728 73Y 749 789 806  
 (72) Inventor RAYMOND MONTAGUE EDWARDS



TC 1700  
 JUL 18 2001  
 RECEIVED

## (54) AN IMPROVED ROOFING MATERIAL

- (71) We, PERMANITE LIMITED, a British Company, of 455 Old Ford Road, London, E.3, do hereby declare the invention, for which we pray that a patent may be granted to us, and the method by which it is to be performed, to be particularly described in and by the following statement:—
- The present invention relates to an improved roofing material in flexible sheet or strip form capable of being rolled for convenience in storage, transport and manipulation when being applied for use, the improved material being particularly suitable for use as a roof lining or underlayer when applied to, for example, the rafters below the slates, tiles or other roof covering to provide a lining or underlayer possessing adequate strength and durability and aiding resistance to weather conditions, and providing heat insulation.
- The roofing material according to the invention comprises a sheet or strip of paper-like flexible absorbent fibre felt made wholly or mainly either of animal and/or vegetable fibres or of asbestos fibres, said felt being impregnated with bituminous material such as bitumen, coal tar pitch or asphalt and covered on one face with a continuous coating or film of a water-impervious synthetic plastics material bonded thereto, the composite sheet or strip of fibre felt and synthetic plastics material bearing on one face thereof a mat or fleece of loosely coherent fibrous insulating material in adhesive contact with the composite sheet or strip.
- The synthetic plastics coating or film may be bonded to the impregnated fibrous felt sheet or strip by an adhesive which may be bitumen or other waterproof material.
- Instead of the coating of synthetic plastics material being applied to the impregnated felt layer as a pre-formed film, the plastics material may be applied in solution, as an emulsion or, in the case of thermoplastic plastics material, in powder form. Heat, which may conveniently be derived from the impregnating agent, is then used to drive off the solvent or the emulsifying agent or to fuse the thermoplastic plastics material so as to form a continuous coating.
- Suitable synthetic plastics materials are polythene or polyvinyl chloride.
- The plastics coating may also be bonded to the impregnated fibrous layer by applying a plastics film to the impregnated felt layer immediately after the impregnation and whilst the impregnating material, for example, bitumen, coal tar pitch or asphalt is still at an elevated temperature and is tacky. In this way it is not necessary to apply a film of adhesive to the impregnated felt layer.
- Whilst the heat for fusing the thermoplastics material or for vaporising the solvent or the emulsifying agent has been described as derived from the impregnated felt layer whilst at elevated temperature, heat may be derived from sources external to the impregnated layer.
- To one face of a composite flexible sheet prepared as described above, there is applied a mat or fleece of loosely coherent fibrous insulating material adhering to the composite sheet.
- The mat or fleece may be applied against the exposed face of either the impregnated felt layer or of the synthetic plastics layer, more usually the latter, and adhesion may be effected by the preliminary application of lines of adhesive, e.g. bitumen, applied hot, or cold in solution in solvent, or as an emulsion to the

BEST AVAILABLE COPY

269 8221

appropriate face of the composite flexible sheet.

- 5 When the mat or fleece is applied against the synthetic plastics film or coating, the other surface of the finished material usually has an additional coating of bituminous material finished with a surfacing of talc.

- 10 As suitable materials for the insulating mat or fleece may be mentioned glass fibre or mineral wool in which the loosely coherent fibres are randomly disposed and the mat or fleece may have a thickness of  $\frac{1}{2}$  inch or more in the unstressed condition of the material.

WHAT WE CLAIM IS:—

- 15 1. A roofing material comprising a sheet or strip of paper-like flexible absorbent fibre felt made wholly or mainly either of animal and/or vegetable fibres or of asbestos fibres, said felt being impregnated with bituminous material and covered on one face with a continuous coating or film of a water-impervious synthetic plastics material bonded thereto, the composite sheet or strip of fibre felt and synthetic plastics material bearing on one face thereof a mat or fleece of loosely coherent fibrous insulating material in adhesive contact with the said composite sheet or strip.

- 20 2. A roofing material as claimed in claim 1 wherein the synthetic plastics coating or film is bonded to the impregnated fibrous felt sheet or strip by means of a waterproof adhesive.

- 30 3. A roofing material as claimed in claim 2 wherein the waterproof bonding material is bitumen.

- 35 4. A roofing material as claimed in any one of the preceding claims wherein the mat or fleece of loosely coherent fibrous insulating material is bonded to the said composite sheet or strip by spaced lines of adhesive applied to one face of the said composite sheet.

- 40 5. A roofing material as claimed in any one

of the preceding claims wherein mat or fleece is adhered to the coating or film of plastics material and the face of the impregnated fibre felt away from the mat or fleece is covered with a supplementary coating of bituminous material finished with a surfacing of talc. 45

6. A roofing material as claimed in any one of claims 1 to 5 wherein the mat or fleece is composed of randomly disposed and loosely coherent glass or mineral fibres and has a thickness of  $\frac{1}{2}$  inch or more in the unstressed condition of the material. 50

7. A method of producing a roofing material which consists in impregnating a sheet or strip of paper-like flexible absorbent fibre felt made wholly or mainly either of animal and/or vegetable fibres or of asbestos fibres with hot bituminous material, applying a pre-formed film, a solution or an emulsion of a synthetic plastics material to one face thereof and heating the synthetic plastics material so that it is bonded or set and bonded to form a continuous water-impervious coating on one face of the impregnated sheet or strip, and adhering a mat or fleece of loosely coherent fibrous insulating material to an exposed face of the resulting composite sheet or strip of fibre felt and synthetic plastics material. 55 60 65

8. A method according to claim 7 wherein the synthetic plastics material is applied before cooling of the impregnated sheet or strip, the residual heat of the impregnated sheet or strip effecting the bonding or setting and bonding of the synthetic plastics material. 70

9. A roofing material according to claim 1 substantially as hereinbefore described. 75

10. A method according to claim 1 substantially as hereinbefore described.

REDDIE AND GROSE.  
Agents for the applicants.

Printed for Her Majesty's Stationery Office by the Courier Press, Leamington Spa, 1971.  
Published by the Patent Office, 25 Southampton Buildings, London, WC2A 1AY, from which copies may be obtained.